

Product: 18 x 12 mm (pre-threaded)

Shell Material

Closure Drawing

Al Composition EN AW-8011A

Al Condition H14

Specific gravity g/cм3 2.71

Tensile strength Rm MPa
Elongation. A50, % min
Anisothropy, % max

H14

2.71

120 - 160

≥ 2

Anisothropy, % max


Material Thickness, mm 0.21 ± 0.01

Closure Characteristics

Outside diameter, mm \varnothing **18.70 \pm 0.3** Height, mm **12.20 \pm 0.2** Inside diameter, mm \varnothing **18.1** Weight without liner, g. **0.50 \pm 5%** Internal lacquer type **Mod. epoxy**

Resins obtained from monomers without any phenols or phtalates.

Mod. epoxy



Stretch wrapped

LINER

Liner material: Foam polyethylene

Liner thickness, mm $1.4 \pm 10\%$ Liner weight, g $0.09 \pm 1\%$

External lacquer type

User has to verify the closures suitability with the specific bottled product and to guarantee the absence of chemical and organoleptic alterations.

Food Contact Approval: All materials intended to come into contact with food are in conformity with the European Community directives, the relevant national regulations and the relevant FDA requirements.

All products comply with Commission directive 94/62/EC concerning heavy metals.

All resins and additives used for inside lacquer production comply with the following Regulations:

- Commission directive 10/2011 relating to plastic materials and articles intended to come into contact with foodstuffs.
- FDA regulation; CFR 21, chapter 175.300 Resinous and polymeric coatings

Packaging specification

Quantity, pcs.

16 000 pcs

Pallet type – Euro pallet

1200 x 800 x*

Box Dimension, mm

* Height of the pallet may vary with customers' requirements

Box Dimension, mm 600 x 400 x 370 mm * Height of the pallet may vary with customers' requirements
Cardboard Type Corrugated five layer cardboard

Polyethylene Sack

Polyethylene –non-toxic, antistatic

Outside packing

<100 ppm Pb, Cd, HgCr⁺⁶

Adhesive Strip (Scotch)

Product Identification

50 mm

Labelling

Pallet identification

Labelling

Notes: Closures shall be stored in a well-ventilated place avoiding direct sunlight and strong odour for the period of 1 year.

Pallets shall not be stacked.